

# PRODUCT INFORMATION

## M-628

### DESCRIPTION

Masking tape for car repair.

### PRODUCT DATA

<b>Backing</b>	58 g/m <sup>2</sup> saturated crepe paper; green
<b>Adhesive</b>	Natural rubber and resins based

	<b>Unit</b>	<b>Value</b>	<b>Method</b>
<b>Total thickness</b>	mm	0.125	PSTC 133
<b>Adhesion to steel</b>	N/25mm	4.3	PSTC 101
<b>Tensile strength MD</b>	N/25mm	85	PSTC 131
<b>Elongation at break</b>	%	8	PSTC 131
<b>Temp. Resistance</b>	°C	80°C (30 min)	=

### APPLICATION

Masking tape suitable for car repair applications when temperature does not exceed 80°C.

<b>Features</b>	<b>Benefits</b>	
Natural rubber and resins based adhesive	<ul style="list-style-type: none"><li>✓ Good adhesion even on irregular surfaces</li><li>✓ Heat resistant up to 80°C (30 min)</li></ul>	<ul style="list-style-type: none"><li>✓ Easy removal without adhesive residue, if removed as soon as paint is dry</li></ul>
Saturated paper backing	<ul style="list-style-type: none"><li>✓ Well conformable to most shaped surfaces</li><li>✓ Compatible with most common paints and lacquers</li></ul>	<ul style="list-style-type: none"><li>✓ Removable without breaking</li><li>✓ Hand tearable</li></ul>

### CONDITIONS OF USE AND CONFORMITY

Product shelf life and storage: 12 months; suggested storage temperature shall range from 15°C to 25°C with max. relative humidity of 65%. Material shall be stored away from heat sources and possibly kept in original package, avoiding light exposure as well. When temperatures are lower than suggested, it is always required to recondition the tape at normal temperature before use. This information is given to the best of Sicad's knowledge. Values are typical and do not constitute a specification. Customers are required to do their own testing under their working condition for their intended application. Any liability arising in respect of our products will be limited to the value of those products charged to the customer excluding any consequential loss.