

3M

Scotch-Grip™

Contact Adhesive

10

Technical Data

November, 2004

Product Description

3M™ Scotch-Grip™ Contact Adhesive 10 is a multi-purpose contact adhesive which may be used to bond plastic laminate, aluminum, steel, wallboard, wood, masonry, rubber and canvas.

Note: Successful bonds with wood veneers, using this product, is dependent on many variables such as environmental conditions, bonding process, type of base material, type of veneer and finishing systems to name a few. It is the user's responsibility to thoroughly test any adhesive for its suitability in bonding wood veneers.

Features

- Roll or brush-applied.
- Fast drying.
- Adhesion to a wide variety of materials.
- Excellent resistance to plastic flow (creep).
- 60 minute bonding range.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Viscosity (approx.)	450-700 cps
Brookfield Viscometer	RVF #2 spindle @ 20 rpm @ 80°F (27°C)
Solids Content (by wt.)	21-25%
Base	Polychloroprene
Color (wet and dry)	Yellow
Net Weight (lbs./gal.)	6.9 ± 0.2 lbs.
Flash Point (TCC)	-14°F (-25°C)
Coverage (approx.)	288 sq. ft. per gallon (@ 2.5 gms./ft. ² dry wt.)
Solvent	Petroleum distillate, acetone, toluene and n-hexane

Scotch-Grip™

Contact Adhesive

10

Handling/ Application Information

Directions For Use

Note: Read and follow precautions before using this product.

Surface Preparation

1. For best results, all surfaces to be bonded should be dry and free from dirt, dust, oil, loose paint, wax, grease, etc.
2. Oil, grease and other contaminants can be removed by wiping with solvents such as 3M™ Scotch-Grip™ Solvent No. 3 or methyl ethyl ketone.*
3. If used for decorative laminate, laminate should have reached moisture equilibrium for the shop conditions.

Working Temperature

1. The temperature of the adhesive and surfaces to be bonded should be at 65°F (18°C) or above.
2. Warm the can of adhesive by placing in a warm room, not in stove, oven or other possible ignition source.
3. If the room must be warmed, turn off the heater before opening container.
4. Leave heater off until all vapors are gone.

Application

1. Stir thoroughly before using.
2. Apply adhesive generously in a uniform film on both surfaces with either a fiber or animal hair brush, or pour and spread with paint roller (solvent resistant texturing type).
3. Porous surfaces may require 2 coats of adhesive.
4. A glossy film when completely dry indicates adequate adhesive.
5. Dull spots after drying indicate not enough adhesive; these spots must have another coat.

Assembly

1. Allow to dry until adhesive is no longer tacky (5-10 minutes).
2. Position surfaces carefully before assembly.
3. No adjustment is possible after contact.
4. Spacers such as dowels or strips of laminate, may be used to prevent premature adhesive/adhesive contact and bonding.
5. Slide out the spacers and apply uniform pressure, working toward the edges.
6. A 3 in. roller used with maximum body pressure should be used to help ensure adequate contact and bonding, especially on the edges.
7. Bonded assemblies can be machined, trimmed or finished immediately after bonding.

Drying Time

1. Drying time depends on temperature, humidity, air movement and porosity of materials bonded.

Cleanup

1. Excess adhesive may be removed with a solvent such as Scotch-Grip Solvent No. 3 or methyl ethyl ketone.*

***Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Scotch-Grip™ Contact Adhesive 10

Application Equipment Suggestions

Note: Appropriate application equipment enhances adhesive performance. We suggest the following application equipment for the user's evaluation in light of the user's particular purpose and method of application.

1. **Brushes:** Use fiber or animal hair brushes. Do not use nylon or other synthetic fibers.
2. **Rollers:** Use solvent resistant paint rollers, designed for applying oil based paints.

Typical Adhesive Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Peel Strength: Peel bonds of cotton duck (canvas) to cold rolled steel were tested at a peel angle of 180°F at two inches per minute separation rate.

Time @ 75°F (24°C)	Test Temp.	Value (lbs./inch width)
1 day	75°F	10
3 days	75°F	13
5 days	75°F	17
1 week	75°F	19
2 weeks	75°F	22
3 weeks	75°F	23
3 weeks	-30°F	28 (substrate failure)
3 weeks	180°F	9

Overlap Shear Strength: Overlap shear strength on birch plywood to itself tested at 0.1 inches per minute separation rate.

Time @ 75°F (24°C)	Test Temp.	Value (psi)
2 weeks	RT	430 (substrate failure)
3 weeks	RT	433 (substrate failure)
3 weeks	-30°F	676 (substrate failure)
3 weeks	180°F	111
3 weeks	225°F	70

Storage

Best storage temperature is 60-70°F (16-27°C). Continuous exposure to higher temperatures may cause some increase in viscosity. Quality is not affected until the adhesives becomes thickened so that it is difficult or impossible to spread. 3M™ Scotch-Grip™ Contact Adhesive 10 will not freeze, but continuous exposure to low temperature will cause a considerable increase in viscosity. After storage at low temperatures and before using, the adhesive must be thawed and stirred vigorously until the entire container regains its original viscosity. The thawing process should be done at approximately room temperatures, never at elevated temperatures. Several days may be required for thawing – particularly with larger containers. Rotate stock on a “first in-first out” basis.

Shelf Life

When stored at the recommended conditions in the original, unopened container this product has a shelf life of 15 months.

Scotch-Grip™ Contact Adhesive 10

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (fax)
www.3M.com/industrial



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2004 78-6900-9882-3 (11/04)