



Membrane Switch Spacer/Data Page

FOD # 0917

Scotch™ 7956MP Membrane Switch Spacer

Description

Liner: 58# Polycoated Kraft
Adhesive: #200 “Hi-Performance” Acrylic
Adhesive Carrier: Polyester Film
Adhesive: #200 “Hi-Performance” Acrylic
Liner: 58# Polycoated Kraft

Typical Applications

Spacer for membrane switch/keyboard circuits

Features

- Long term environmentally stable bond.
- High cohesive strength to withstand repeated stresses from switch activation.
- Excellent temperature, humidity, and chemical resistance.
- High bond strength to high surface energy plastics such as polyester and polycarbonate.

<u>Component</u>	<u>Description</u>	<u>Appropriate Thickness</u>	
		<u>Inches</u>	<u>(MM)</u>
Release Liner	58# Polycoated Kraft	0.004	0.10
Adhesive	#200 “Hi-Performance” Acrylic	0.002	0.05
Adhesive Carrier	Polyester	0.002	0.05
Adhesive	#200 “Hi-Performance” Acrylic	0.002	0.05
Release Liner	58# Polycoated Kraft	0.004	0.10
	Total Thickness	0.014	0.35

Properties and Performance

(Typical Values – Not for Specification Use)

- Temperature Range
 - Low – –40 degrees F (–40 degrees C)
 - High Long Term (days, weeks) 250 degrees F (121 degrees C)
 - High Short Term (minutes, hours) 300 degrees F (149 degrees C)
- Chemical Resistance
 - Solvent resistance is excellent when this product is properly applied to impervious materials. The adhesive resists softening through edge contact with mild acids, alkalies, oil, gasoline, Kerosene, JP-4 fuel and many other solvents.
 - Not recommended for total immersion
- Dielectric Strength (ASJM D149)

1.6	KV/mil
	14
- Insulation Resistance (ASTM P257)

1.2 x 10	ohms
	15
- Volume Resistivity (ASTM D257)

8.6 x 10	ohm-cm
	14
- Surface Resistivity (ASTM D257)

4.4 x 10	ohms/square
----------	-------------
- Moisture and Humidity Resistance

No adverse effect on the bond after exposure to 100% RH at 100 degrees F.
- Shelf Life

Twelve months from date of receipt by customer when stored in cartons at 70 degrees F at 50% relative humidity.
- Bond Build-Up

The bond strength of Scotch #200 “Hi-Performance” Acrylic Adhesive increases as a function of time and temperature.
- U.V. Resistance

Adhesive is resistant to oxidation and ozone when exposed to air or sunlight (U.V.).

Adhesion Properties

The results indicated are typical values:

	7956MP			
	<u>OZ/IN</u>		<u>N/100 mm</u>	
ASTM D903 180 degree peel 12"/minute 1 mil polyester to stainless steel	85		94	
3M test 90% peel 12"/minute 8 mil aluminum to various surfaces	72 Hour Dwell		Ultimate Bond	
	<u>OZ/IN</u>	<u>N/100 mm</u>	<u>OZ/IN</u>	<u>N/100 mm</u>
Stainless Steel	106	116	98	108
Epoxy	112	124	90	100
Polyester	100	110	78	86
Polycarbonate	126	140	128	140
ABS	134	146	86	96

Application Properties

1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.
2. To obtain optimum adhesion, the bonding surfaces must be clean, dry, and smooth. Some typical surface cleaning solvents are isopropyl alcohol or heptane. Use proper safety precautions for handling solvents.
3. Ideal tape application temperature range is 70 degrees F. to 100 degrees F. (21 degrees C. to 38 degrees C.). Initial tape application to surfaces at temperatures below 50 degrees F. (10 degrees C.) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

4/1/96

Terms and Conditions of Sale for products sold by 3M Identification and Converter Systems Division can be found in the ICSD Price Book and in other appropriate schedules.

Technical Data: All physical properties, statements, and recommendations are either based on tests we believe to be reliable or our experience, but they are not guaranteed. 3M recommends each user determine the suitability of the products for the intended use.

Warranty and Limited Remedy: THE FOLLOWING WARRANTY IS MADE IN LIEU OF ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE AND ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, A CUSTOM OR USAGE OF TRADE: 3M warrants its product will be free from all defects.

If a product is proved to be defective, then the exclusive remedy 3M's and seller's sole obligation shall be, at 3M's option, to replace the quantity of the product which is proved to be defective or to refund the purchase price.

Limitation of Liability: 3M and seller shall not be liable for direct, indirect, special, incidental or consequential damages based breach of warranty, breach of contract, negligence, strict liability or any other legal theory.

The foregoing Warranty and Limited Remedy and Limitation of Liability may be changed only by a written agreement signed by authorized officers of 3M and seller.

Scotch, ScotchMark, ScotchCap, and Stamark are trademarks of 3M.



**Identification and Converter
Systems Division**

3M Center, Building 220-7W-03
St. Paul, MN 55144-1000
USA
1 800 223 7427
1 800 258 7511 FAX
e-mail idconvert@mmm.com

3M Canada Inc.

PO Box 5757
London, Ontario
Canada N6A 4TI
1 800 265 1840
519 452 6090 FAX

3M Mexico, S.A. de C.V.

Apartado Postal 14-139
Mexico, D.F. 07070
Mexico
52 5 728 2289
52 5 728 2299 FAX

3M Puerto Rico, Inc.

Puerto Rico Industrial Park
PO Box 100
Carolina, PR 00986-0100
809 750 3000
809 750 3035 FAX