

# Data Page

Issue Date 8/01/97

## 3M™ 9653LE, 9671LE, 9672LE Laminating Adhesives

### Features:

- High-strength 3M™ 300LSE Acrylic Adhesive provides very high bond strength to most surfaces.
- Excellent bond to low surface energy plastics such as, polypropylene and powder coatings.
- Excellent adhesion to surfaces contaminated lightly with oil typically used with machine parts.
- Thickness range of 2.0 mils, 3.5 mils and 5.0 mils for use on smooth, rough and textured surfaces.
- Extremely smooth adhesive for excellent graphics appearance.
- 6.5 mils Polycoated kraft liner for die-cutting end tabs and waste removed nameplates on a common carrier.
- Polycoated kraft liner for lay flat, moisture stability and excellent processing of plastic graphic overlays.

### Applications:

- Plastic nameplates or graphic overlays for use on low surface energy plastics.
- Waste removed nameplates on a common sheet for ease of application.

### 3M Identification and Converter Systems Division

3M Center, Building 220-7W-03  
St. Paul, MN 55133-32220  
U.S.A.  
1-800-328-1681

Table 1. **Product Construction:**

3M™ Laminating Adhesive	Adhesive (Solvent Free)	Liner
9671LE	2.0 mils (51 microns) 3M 300LSE High-strength Acrylic Adhesive	6.5 mils (163 microns) 86# Polycoated kraft
9653LE	3.5 mils (88 microns) 3M 300LSE High-strength Acrylic Adhesive	6.5 mils (163 microns) 86# Polycoated kraft
9672LE	5.0 mils (127 microns) 3M 300LSE High-strength Acrylic Adhesive	6.5 mils (163 microns) 86# Polycoated kraft

Table 2. **Typical Adhesion Chart:**

	3M™ Laminating Adhesive	15 Minute Room Temperature		72 Hour Room Temperature	
		Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	9671LE	71	78	75	82
	9653LE	90	98	100	109
	9672LE	109	119	140	153
ABS	9671LE	70	77	79	86
	9653LE	80	88	113	124
	9672LE	102	112	128	140
Poly-propylene	9671LE	69	75	74	81
	9653LE	89	97	103	113
	9672LE	115	126	136	149

- Attaching membrane switch assemblies to powder coated surfaces and low surface energy plastics.
- Graphic overlays with end tabs for easy liner removal.
- Graphic application to surfaces such as wood, fabric, plastic, where very high bond strength is required.

- Attaching identification material to lightly oily surfaces typical of machine parts.

### Typical Adhesion Properties:

**NOTE:** The above technical information and data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion - ounces/inch (Newtons/100 mm) ASTM D3330, modified: 90° peel, 2 mil aluminum backing

**Environmental Performance:**

The properties defined are based on the attachment of impervious faceplate materials (such as aluminum) to a stainless steel test surface.

**Bond Build-up:** The bond strength of 3M™ 300LSE High-strength Acrylic Adhesive increased as a function of time and temperature, and has very high initial adhesion.

**Humidity Resistance:** High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

**U.V. Resistance:** When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

**Water Resistance:** Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

**Temperature Cycling Resistance:** High bond strength is maintained after cycling four times through:

4 hours at 158°F (70°C)

4 hours at -20°F (-29°C)

4 hours at 73°F (22°C)

**Chemical Resistance:** When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

**Temperature Resistance:** The 3M 300LSE High-Strength Acrylic Adhesive is usable for short periods (minutes, hours) at room temperatures up to 300°F (148°C) and for intermittent longer periods of time (days, weeks) up to 200°F (93°C).

**Low Service Temperature:** -40°F (-40 °C)

**Shelf Life:** Product retains its performance and properties for two years from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity. Storage in plastic bag is recommended.

**Processing:**

**Slitting and die-cutting:** This adhesive is very aggressive and may be difficult to die-cut. Chilling the adhesive between 35°F and 50°F will improve the processability. In addition, dies can be lubricated with Laminoleum evaporative stamping oil which is available from Metal Lubricants Company (708-333-8900) or Lubri-Blade 907 from Ceramic Technologies Inc. (800-258-8495).

**Roll Laminating:** A combination of metal and rubber rollers with moderate pressure is recommended.

\*\* Please refer to the **3M Slitting/ Die-cutting Technical Bulletin** for further details.

**Special Considerations/ Application Tips:**

For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Consult solvent manufacturer's Material Safety Data Sheet for proper handling and storage instructions.

Bond strength can also be improved with firm application pressure and moderate heat, from 100°F (38°C) to 130°F (54°C), causing the adhesive to develop intimate contact with the bonding surface.

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure-sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

**3M Identification and Converter Systems Division**

3M Center, Building 220-7W-03  
St. Paul, MN 55133-32220  
U.S.A.  
1-800-328-1681

**Terms and Conditions of Sale** for products sold by 3M Identification and Converter Systems Division can be found in the ICSD Price Book and in other appropriate price schedules.

**Technical Data:** All physical properties, statements, and recommendations are either based on tests we believe to be reliable or our experience, but they are not guaranteed. 3M recommends each user determine the suitability of the products for the intended use.

**Warranty and Limited Remedy:** THE FOLLOWING WARRANTY IS MADE IN LIEU OF ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE AND ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, A CUSTOM OR USAGE OF TRADE: 3M warrants its products will be free from all defects. If a product is proved to be defective, then the exclusive remedy and 3M's and seller's sole obligation shall be, at 3M's option, to replace the quantity of the product which is proved to be defective or to refund the purchase price.

**Limitation of Liability:** 3M and seller shall not be liable for direct, indirect, special, incidental or consequential damages based upon breach of warranty, breach of contract, negligence, strict liability or any other legal theory.

The foregoing Warranty and Limited Remedy and Limitation of Liability may be changed only by a written agreement signed by authorized officers of 3M and seller.

For Customer Service and Product Information, call **1-800-328-1681**.



**Identification and Converter Systems Division**

3M Center, Building 220-7W-03  
St. Paul, MN 55144-1000  
USA  
1 800 223 7427 Fax On Demand  
1 800 258 7511 FAX  
e-mail [ldconvert@mmm.com](mailto:ldconvert@mmm.com)  
3M Web Site: <http://www.mmm.com>

**3M Canada Inc.**

PO Box 5757  
London, Ontario  
Canada N6A 4T1  
1 800 265 1840  
519 452 6090 FAX

**3M do Brasil Ltda – Cepi 23050**

Caixa Postal 123  
Campinas – SP – Brazil  
Cep. 13001-970  
55 19 864 7143  
55 19 864 7637 FAX

**3M Puerto Rico, Inc.**

Puerto Rico Industrial Park  
PO Box 100  
Carolina, PR 00986-0100  
809 787 3000  
809 787 3035 FAX

**European Business Unit  
Identification and Converter Systems  
c/o 3M Deutschland GmbH**

Carl-Schurz-StraBe 1  
D-41453 Neuss  
+49 (0) 21 31/14 39 26  
+49 (0) 21 31/14 36 95 FAX

**3M Mexico, S.A. de C.V.**

Apartado Postal 14-139  
Mexico, D.F. 07070  
Mexico  
52 5 728 2289  
52 5 728 2299 FAX

**3M Asia Pacific Pte. Ltd.**

9, Tagore Lane  
Singapore 787472  
Republic of Singapore  
++65 4508871  
++64 4585432 FAX