3M

Bumpon[™] Protective ProductsClear Polyurethane Rollstock

5600 Series

Page 1 of 4

Technical Data		March, 1995	
Product Description	SJ-5632 SJ-5616	1/32 in. (0.8 mm) 1/16 in. (1.6 mm)	
	SJ-5608	1/8 in. (3.2 mm)	
	Resilient 70 du pressure sensit	urometer clear polyurethane sheet product utilizing an aggressive acrylic-based, ive.	
Features	Transparent – universal color match.		
	Excellent resistance to yellowing		
	 Can be die cut to a variety of shapes and sizes. 		
	 Excellent resistance (Resulting from a urethane composition which contains no 		
	plasticizers.) to marring or staining.		
	 Long aging resiliency – will not crack or harden 		
	• Excellent cushioning properties.		
	• Excellent abrasion resistance.		
	Vibration and shock damping		
	• Easy application – pressure sensitive adhesive backing.		
Application Ideas	• Die cut shap	pes for glass table taps, cushioning glass from metal and wood frames.	
	 Die cut shapes for use as cushions and spacers on cabinet doors, drawers, and lids. 		
	• Die cut shapes for use as skid-resistant feet on small appliances and desk top equipment.		
	• Die cut shapes for use as cushions and pads in glass or clear plastic ahelves.		
	 Strips or pads for use as skid-resistant surfaces in glass or clear plastic shelves. 		
	Antichafe protection.		
	Corner protection strips.		
	 Door kick p 	a da	

Product Constructions

Products	SJ-5632	SJ-5616	SJ-5608
Material:	Clear polyurethane		
Release Liner:	White 110 lb./ream silicone paper		
Adhesive:	A-20 (acrylic)		
Color:	Transparent		
Thickness:*	1/32 in. 0.031 in (0.8 mm)	1/16 in 0.062 in. (1.6 mm)	1/8 in. 0.125 in. (3.2 in.)

Bumpon[™]**Protective Products**

Clear Polyurethane Rollstock

5600 Series page 2 of 4

Thickness Tolerance: ±(inches) ±(mm)	0.010 0.25	0.015 0.38	0.020 0.51
Roll Length:	72 yds.	36 yds.	36 yds.
Roll Widths:	4.5 in (114.3 mm)	4.5 in, (114.3 mm)	4.5 in. (114.3 mm)
Slitting Tolerance: ± inches		0.031	
		(0.8)	

^{*}ASTM-D-D-3767 procedure A (3.2 psi) measured without liner.

Special Products of the Design-A-Bump Program

3M can customize thickness to your specifications. Call your 3M industrial Tape and Specialties Division Sales Representative for details. Custom products require a minimum order quantity.

The thickness capability range for 5600 series Rollstock is 1/32 in. minimum and 1/8 in. maximum

Typical Physical Performance Characteristics

Note: The following technical information and data should be considered representative or Typical only and should not be used for specification purposes.

Acrylic (A-20) – This high strength adhesive provides excellent shear properties at elevated temperatures. The adhesive adheres well to glass, many metal surfaces, some paints, and many high surface energy plastics (Formica®, ABC, polycarbonate, etc.) **Note**: This adhesive is not recommended for use on use on low surface energy plastics (polypropylene, polyethylene, etc.)

Static Shear Adhesive Performance

Temperature Tested at:	Time to Failure, minutes
75°F (24°C)	> 10,000
120°F (49°C)	> 10,000
158°F (70°C)	> 10,000
180°F (82°C)	> 10,000

One in. overlap shear test; ASTM-D-3654-M (1000 gram); testing completed on stainless steel test panels using SJ-5616 protector.

90 ℃ Peel Adhesion Performance

Substrate	Peel Force, oz. Per 1/2 in
Polypropylene	3
Polystyrene	11
ABS	25
Stainless Steel	25
Aluminum	25
Glass	25

3M Test Method TM-2011;72 hour dwell, 1/2 in. wide samples pulled at 12 in. per minute. Testing completed using SJ-5616 protector.

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Peoperty	Test Method	Test Results
Hardness, Shore A	ASTM-D-2240	70
Approximate Density, lb./ft. ² (gm/ cm ³)		70 (1.1)
Resilience, %	ASTM-D-2632	.6
Kinetic Coefficient of Friction*		
	ASTM-D-1894	>1
	Glass, Stainless Steel Formica®	>1
Abrasion Resistance, gm/1000 cycles	ASTM-C-501:Tabor H,1 kg	0.13
Tensile, lb./in. ² (kPa)	ASTM-D-412, Die A	740 (5100)
Elongation, %	ASTM-D-412, Die A	65

Bumpon[™]Protective Products

Exposure:

Clear Polyurethane Rollstock

5600 Series page 3 of 4

Stain Resistance	3M-24hrs. at 158°F against white paint1 7 days exposed to UV	No staining
Solvent Resistance	3M –24 hr. immersion 5% Detergent in water 25% Detergent in water 5% Bleach in water Gasoline Motor Oil Isopropyl Alcohol	No apparent effect No apparent effect No apparent effect Slight swelling No apparent effect Slight swelling
of the area of conta surfaces. Thus, if the	s of friction applicable to Bumpon brand Rollstock and the between solids and (2) friction is proportional to the load(weight) is doubled the force required to caust pressed mathematically as follows:	the load between solids
	Slide force = (kinetic coefficient of friction) \times (we	ight)
Load Tolerance:	The "recommended" maximum load which 5600 series Rollstock will support is 100 psi (690 kPa) at $70^{\circ}F(21^{\circ}C)$ to $120^{\circ}F(46^{\circ}C)$.	
Shelf Life:	Shelf life is 18 months from date of manufacture when stored in original cartons at 60-80°F (15-27°C) and 40-50% relative humidity.	
Environmental	Clear Rollstock is intended for interior applicatio	ns where resilience and all

Application Ideas

To obtain maximum adhesion, surfaces must be unified, dry, and free of contaminants. Surface contact is fundamental to adhesive performance. To maximize contact on a substrate:

other physical properties will remain unchanged. When exposed to UV light

for extended periods, some discoloration may occur. Clear Rollstock may be

used outdoors in a protected area with some discoloration possible. Simultaneous exposure to high humidity and temperature may degrade

· Clean surfaces with low strength solvents such as isopropyl alcohol (rubbing alcohol) or heptane.

Note: Be sure to follow the solvent's manufacturer's precautions and directions for use when using solvents.

• Apply firm pressure to increase the cold flow and contact of the adhesive with the substrate.

(soften) the product composition.

• Allow time (dwell) to increase the surface contact and adhesion.

Application Temperature: $+40^{\circ}F$ (5 $^{\circ}C$) to $125^{\circ}F$ (52 $^{\circ}C$) Service Temperature: $-30^{\circ}F$ (-34 $^{\circ}C$) to $150^{\circ}F$ (66 $^{\circ}C$)

225°F(107°C) intermittent exposure

Note: Product selection is ultimately the user's responsibility. Users should conduct their own tests under actual use and storage conditions to determine whether the product is fit for a particular purpose and method of application.

Bumpon[™]Protective Products

Clear Polyurethane Rollstock

5600 Series page 4 of 4

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-227-5085. Address correspondence to: 3M, Industrial Tape and Specialties Division, 3M Center, Building 220-8E-04, St. Paul, MN 55411-1000. Our fax number is 612-733-9175. in Canada, phone: 1-519-451-2500. in Puerto Rico, phone:1-809-750-3000. in Mexico. Phone: 5-728-0400.

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILTY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M ITSD product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M ITSD product. Given the variety of factors that can affect the use and performance of a 3M ITSE product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M ITSD product to determine whether it is fit for a particular purpose and suitable for the user's method application.

Limitation of Remedies and Liability

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.



This Industrial Tape and Specialties Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

